

HARBOURITE - 12mm

SPECIFICATION

Fibres shall be HARBOURITE 12mm fine fibrillated polypropylene fibres manufactured to ISO 9002 Quality Assured Standards from pure polypropylene to ISO 1873-PP-H, FN, 28-02-045 supplied by: Synthetic Industries Europe (Tel: + 44 (0)1246 564200).

The fibres should be designed specifically for use in mortars and screeds.

Unless otherwise stated HARBOURITE 12mm fine fibrillated fibres shall be mixed at the batch plant, at the recommended rate of 0.9kg (1 bag) per tonne of mix, and mixed for sufficient time (Min. 5 minutes at full mixing speed after the addition of fibres) to ensure uniform distribution of the HARBOURITE fibres throughout the mix.

NOTES

1. *HARBOURITE fine fibrillated fibres can be added to all mortars/screeds without any change to the mix design.*
2. *HARBOURITE fine fibrillated fibres are chemically inert and are therefore unaffected by the addition of admixtures or additives to the mix.*
3. *The services of SI Concrete Systems Area Sales Manager are available to Specifiers, Contractors and Concrete Producers on request.*

Please ensure you have up-to-date information. SI Concrete Systems reserve the right to alter publications, without notification, in the light of continuing research and development.



SI Concrete Systems

Hayfield House, Devonshire Street,
Chesterfield, Derbyshire, S41 7ST. UK.

Tel: + 44 (0)1246 564200 Fax: + 44 (0)1246 564201

E-mail: fibermesh@sind.co.uk

www.siconcretesystems.com

